

LARGE ORBITAL MAGNETIC MOMENT IN FeBr_2

Z.Ropka

Center for Solid State Physics, Św. Filip 5, 31-150 Kraków, POLAND.

R. Michalski

*Center for Solid State Physics, Św. Filip 5, 31-150 Kraków.
Inst. of Physics, Pedagogical University, 30-084 Kraków, POLAND.*

R. J.Radwanski

*Center for Solid State Physics, Św. Filip 5, 31-150 Kraków.
Inst. of Physics, Pedagogical University, 30-084 Kraków, POLAND.*

Magnetic moment of the Fe^{2+} ion in FeBr_2 has been calculated to be $4.32 \mu_B$ in the magnetically-ordered state at 0 K. It is composed from the spin moment of $3.52 \mu_B$ and the orbital moment of $+0.80 \mu_B$. These calculations show that for the meaningful analysis of e-m properties of FeBr_2 the spin-orbit coupling is essentially important and that the orbital moment is largely unquenched.

PACS 75.10.Dg 71.70.Ch 71.28+d 75.30.Mb

Keywords: crystal-field interactions, spin-orbit coupling, Fe^{2+} ion, FeBr_2

FeBr_2 exhibits the strong metamagnetic properties [1,2]. At 4.2 K an external field of 3.15 T causes a jump of the magnetization from the almost zero value to a very big value of 110 emu/g [1,2]. This latter value corresponds to $4.4 \mu_B$ per the iron-ion moment. This value exceeds a theoretical value of $4.0 \mu_B$ expected for the spin-only moment. The explanation of this large magnetic moment is a subject of long-time debate within the 3d-magnetism theoreticians [3-9].

We have calculated the atomic-like magnetic moment of the Fe^{2+} ion in the ionic FeBr_2 compound to be $4.32 \mu_B$ in the magnetically-ordered state at 0 K. This moment is composed from the spin moment of $3.52 \mu_B$ and the orbital moment of $+0.80 \mu_B$. In the paramagnetic state the total moment amounts to $4.26 \mu_B$ (3.48 and $0.78 \mu_B$).

The calculations have been performed within the quantum atomistic solid-state theory, that points out the existence of the discrete energy spectrum in the 3d-ion containing compounds associated with quasi-atomic 3d states. We have considered 6 d electrons of the Fe^{2+} ion to form the highly-correlated atomic like electronic system $3d^6$. Such the system is characterized by $L=2$ and $S=2$ [10-12]. We have taken into account the crystal field (CEF) interactions (cubic CEF parameter $B_4 = +200$ K, off-cubic trigonal distortion parameter $B_2^0 = -30$ K) and the intra-atomic spin-orbit coupling ($\lambda_{s-o} = -150$ K).

The crystal-field interactions in the hexagonal structure of FeBr_2 cause the Fe-ion moment to lie along the hexagonal axis. The hexagonal axis is the trigonal axis of the local Br^{1-} octahedron. As a consequence the antiferromagnet FeBr_2 is very good example of the Ising-type magnetic compound. The metamagnetic transition is associated with the reversal of the AF moment. The Fe^{2+} -ion moment strongly depends on the local symmetry. The local symmetry is reflected in the symmetry of the CEF. The low-temperature magnetic moment can vary from the zero value to almost $6 \mu_B$ as the function of the local surrounding of the Fe^{2+} ion. The zero value is the manifestation of the Kramers and Jahn-Teller theorems for the highly-correlated electronic system with the even number of involved electrons.

In conclusion, the Fe^{2+} ion in FeBr_2 exhibits large atomic-like magnetic moment with the very substantial orbital magnetic moment. The derived electronic structure exhibits the discrete energy spectrum, like in Refs 6 and 13 (the Co^{3+} ion is equivalent to the Fe^{2+} ion), in contrary to the presently-in-fashion results with the continuous energy spectrum for the 3d states [7-9].

-
- [1] M.K.Wilkinson, J.W.Cable, E.O.Wollan and W.C.Koehler, Phys.Rev. 113 (1959) 497.
 - [2] L.S.Jacobs and P.E.Lawrence, Phys.Rev. 164 (1967) 866.
 - [3] H.Aruga Katori, K.Katsumata and M.Katori, Phys.Rev. B 54 (1996) R9620.
 - [4] M.Pleimling and W.Selke, Phys.Rev. B 56 (1997) 8855.
 - [5] K.Katsumata, H.Aruga Katori, S.M.Shapiro and G.Shirane, Phys.Rev. B 55 (1997) 11466.
 - [6] R.J.Birgenau, W.B.Yelon, E.Cohen and J.Makovsky, Phys.Rev. B 5 (1972) 2607.

- [7] Zhong Fang, I.V.Solovyev, H.Sawada and K.Terakura, Phys.Rev. B 59 (1999) 762.
- [8] D.G.Isaak, R.E.Cohen, M.J.Mehl and D.J.Singh, Phys. Rev. B 47 (1993) 7720.
- [9] P.Ravindran, P.A.Korzhavyi, H.Fjellvag and A.Kjekshus, Phys.Rev. B 60 (1999) 16423.
- [10] C.Kittel, Introduction to Solid State Physics (John Wiley & Sons, Inc., New York 1996), ch.14 and 15; N.W.Aschroft and N.D.Mermin, Solid State Physics (1976) ch. 31.
- [11] A.Abragam and B.Bleaney, in: Electron Paramagnetic Resonance of Transition Ions, (Clarendon Press, Oxford) 1970.
- [12] R.J.Radwanski and Z.Ropka, Relativistic effects in the electronic structure for the 3d paramagnetic ions, <http://xxx.lanl.gov/abs/cond-mat/9907140>.
- [13] R.J.Radwanski and Z.Ropka, Physica B 281&282 (2000) 507.

Figure captions:Fig.1. The calculated temperature dependence of the local magnetic moment of the Fe^{2+} ion in FeBr_2 together with the spin and orbital contributions.

